

CLASSIC LINE

SATINÉ

Matt primer

CODE 11-301

DESCRIPTION AND USE

Alkyd-based primer with high coverage and filling properties. It has good adherence and it is easy to sand. It is normally used for the preparation of wood to synthetic enamel applications. Aspect of the dry film: flat

APPLICATION DATA**30 min**
DRY TO TOUCH**12h**
RECOAT TIME**8 m²/l**
SPREAD RATE**TECHNICAL DATA**

COMPOSITION	Based on alkyd resins, pigments and selected charges
SPECIFIC GRAVITY	1.620 ± 0.030 Kg/l
FLASH POINT	Over 21°C
SOLIDS BY VOLUME	59%
V.O.C.	385 g/L
AVERAGE VISCOSITY	2.8 Poises (Cone/Plate at 20°C)
FILM THICKNESS	Dry: 40 – Wet: 70
FINENESS OF GRIND	25 microns
COLOURS	Matt white
PACKAGING	2500 ml – 500 ml – 250 ml
STORAGE	Keep from freezing. Store in a cool, dry place with adequate ventilation.

APPLICATION GUIDE

Surface preparation:

Apply one coat of thinned product following the instructions given above. Fill holes and cracks with Stucco a Spatola. After 24 hours sand and apply a second coat of Satinè. Finally apply the finish desired.

Orazio Brignola S.p.A. reserves the right to update the above data, which are given for information only. If products are not used beyond our control our liability is limited to the quality of the product itself